

AZAHAR

Inspiration for those who are looking for a soft range of colors but with a strong presence.

The warm range of colours and its strong presence make this fabric the best option to give the touch of distinction that you are looking for to dress your windows.



Azahar

OF= 1-5%



R85 Jute Parchment



R86 Jute Flax




R87 Jute Latte




R89 Chenille Marshmallow



R90 Chenille Pearl



R92 Chenille Driftwood



Q43 Marble Sand

Azahar

OF=1-5%

Fabric

Type of fabric	49% Polyester, 51% PVC
Weave pattern	Basket Weave
Widths	250 cm
Roll length	27.4 ml

Technical specifications	Average values	Standar
Weight	528 g/m ²	ASTM D 1777 : 1996
Thickness	1.38 mm	ASTM D 3776 : 2009
Fire resistance*	Class A rating	NFPA 101 - USA norm
Color fastness (scale blue)	≥7	ISO 105 b02 : 2000
Ultra violet blocking	97%	AATCC 183 : 2010
Antibacterial	complies	ASTM G21
Lead free	complies	REACH Regulation
Environment	complies	Standard 100
Acoustic	under testing	Greenguard
Warranty	5 years	ASTM C423-09a

Processing

Cutting	Crush cut, Ultrasonic
Welding	Thermal, HF, Ultrasonic, Sewing.
Cleaning	Remove dust with soft brush or soft sponge and clear water.

Additional information



5 years warranty



Energy saving



Easy maintenance



Indoor comfort



Printable



Flame retardant



Lead free











These properties are given as indicate and don't have any contractual value.

*For other international test, please contact us.

Azahar

OF=1-5%

Elegance Collection		Solar Heat & Light Control				Gtot			
Article	Color	Ts	Rs	As	Tv	A	B	C	D
R85 Jute Parchment		13	70	17	10	0.32	0.34	0.34	0.25
R86 Jute Flax		30	56	14	27	0.43	0.43	0.39	0.26
R87 Jute Latte		24	50	26	21	0.45	0.45	0.41	0.27
R89 Chenille Marshmallow		16	67	17	15	0.34	0.36	0.35	0.25
R90 Chenille Pearl		32	53	15	29	0.45	0.44	0.40	0.26
R91 Chenille Honey		26	47	27	24	0.47	0.47	0.42	0.27
R92 Chenille Driftwood		12	26	62	14	0.58	0.57	0.49	0.29
Q43 Marble Sand		9	48	43	9	0.44	0.45	0.41	0.27

Ts: Solar transmission Rs: Solar Reflection As: Solar absorption Tv: Visible light transmission Gtot: Total solar energy transmittance